

SICOMET®

Sicomet® 8300

April 2011

PRODUCT DESCRIPTION

Sicomet® 8300 provides the following product characteristics:

Technology	Cyanoacrylate
Chemical Type	Ethyl cyanoacrylate
Appearance	Transparent, colorless liquid
Components	One part - requires no mixing
Viscosity	Low
Cure	Humidity
Application	Bonding
Key Substrates	Plastics, Rubbers and Metals

Sicomet® 8300 is a low viscous, very fast curing cyanoacrylate instant adhesive. The product is designed for very fast fixturing and fast bonding of rubber and plastics with high strength. The good flowing behaviour allows an optimal wetting of the surface. By the low viscosity a very thin layer thickness can be achieved during the joining. Both solid and foam rubber sections are joinable with an extensive resistance to aging. The product can be used up to +80 °C operation temperature and at short-term load up to +100 °C.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Density, ISO 12185, g/cm³	1.05 to 1.1
Viscosity, Cone & Plate rheometer, , mPa·s (cP):	
Temperature: 20 °C, Shear Rate: 3,000 s⁻¹	9 to 30
Viscosity, Brookfield, 20 °C, mPa·s (cP):	
Spindle 3, speed 100 rpm	25 to 40
Flash Point - See MSDS	

TYPICAL CURING PERFORMANCE

Under normal conditions, the atmospheric moisture initiates the curing process. Although full functional strength is developed in a relatively short time, curing continues for at least 24 hours before full chemical/solvent resistance is developed.

Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The table below shows the fixture time achieved on different materials at 22 °C / 50 % relative humidity. This is defined as the time to develop a shear strength of 0.1 N/mm².

Fixture Time, seconds:

Aluminum	20 to 35
EPDM	<5
Rubber, nitrile	<15
ABS	2 to 10
Polycarbonate	10 to 20

TYPICAL PERFORMANCE OF CURED MATERIAL

After 72 hours @ 22 °C

Lap Shear Strength, ISO 4587:

Steel (grit blasted)	N/mm² 16 to 26 (psi) (2,320 to 3,770)
Aluminum (grit blasted)	N/mm² 16 to 20 (psi) (2,320 to 2,900)

Zinc dichromate	N/mm² 3 to 8 (psi) (430 to 1,160)
ABS	N/mm² 4.5 to 7 (psi) (650 to 1,010)
Polycarbonate	N/mm² 8 to 15 (psi) (1,160 to 2,170)
Polyamide (6.6)	N/mm² 4 to 7 (psi) (580 to 1,010)
Tensile Strength, ISO 6922:	
Nitrile	N/mm² >5 (psi) (720)

After 24 hours @ 22 °C

Tensile Strength, ISO 6922:

EPDM	N/mm² 2.1 to 2.5 (psi) (305 to 360)
------	--

After 7 days @ 70 °C

Tensile Strength, ISO 6922:

EPDM	N/mm² 2.1 to 2.5 (psi) (305 to 360)
------	--

After 10 seconds @ 22 °C

Tensile Strength, ISO 6922:

Nitrile	N/mm² ≥4 (psi) (580)
---------	-------------------------

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use:

1. For best performance bond surfaces should be clean and free from grease.
2. This product performs best in thin bond gaps (0.05 mm).
3. Excess adhesive can be wiped away with organic solvent.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2